AMENDMENT OF SOLICITATION/MODIFICATION OF CONTRACT			1. CONTRACT	1. CONTRACT ID CODE		PAGE OF PAGES	
	ATTON/MODIF	ICATION OF CONTRACT	J		1	3	
AMENDMENT/MODIFICATION NO.	3. EFFECTIVE DATE	4. REQUISITION/PURCHASE REQ. NO.	•	5. PROJECT	NO.(If applicab	le)	
0001	17-Mar-2004	W38XDD-4058-9657					
6. ISSUED BY CODE  US ARMY CORPS OF ENGNASHVILLE DISTRICT CELRN-CT, ROOM A604 110 NINTH AVE. SOUTH P O BOX 1070 NASHVILLE TN 37202-1070		7. ADMINISTERED BY (If other than item 6)  CONTRACTING DIVISION (JWP)  EMAIL: JAMES.W. PURCELL@USACE.ARMY TEL: 615/736/7569  FAX: 615/736/7124  NASHVILLE TN 37202-1070	CO .MIL	DE H3P	20000		
NASTIVILLE TN 37202-1070		1					
8. NAME AND ADDRESS OF CONTRACTOR	(No., Street, County, S	tate and Zip Code)	x 9A. AMENDM W912P5-04-T	ENT OF SC -0026	DLICITATIO	N NO.	
			X 9B. DATED (S 10-Mar-2004	EE ITEM 1	1)		
			10A. MOD. OF	CONTRAC	CT/ORDER I	NO.	
			10B. DATED (	SEE ITEM	13)		
CODE	FACILITY CO						
X The above numbered solicitation is amended as set forth in It		PPLIES TO AMENDMENTS OF SOLICIT	is extended,	is not exte	. 1. 1		
Offer must acknowledge receipt of this amendment prior to t (a) By completing Items 8 and 15, and returning or (c) By separate letter or telegram which includes a referen RECEIVED AT THE PLACE DESIGNATED FOR THE RI REJECTION OF YOUR OFFER. If by virtue of this amend provided each telegram or letter makes reference to the solic	copies of the amendmen ce to the solicitation and amend CCEIPT OF OFFERS PRIOR T ment you desire to change an o	t; (b) By acknowledging receipt of this amendment on each dment numbers. FAILURE OF YOUR ACKNOWLEDGN O THE HOUR AND DATE SPECIFIED MAY RESULT ffer already submitted, such change may be made by telegi	n copy of the offer submitte MENT TO BE IN	d;			
12. ACCOUNTING AND APPROPRIATION DA	ATA (If required)						
		O MODIFICATIONS OF CONTRACTS/O CT/ORDER NO. AS DESCRIBED IN ITEM					
A. THIS CHANGE ORDER IS ISSUED PURS CONTRACT ORDER NO. IN ITEM 10A.				DE IN THE	,		
B. THE ABOVE NUMBERED CONTRACT/O office, appropriation date, etc.) SET FORTI				changes in p	paying		
C. THIS SUPPLEMENTAL AGREEMENT IS							
D. OTHER (Specify type of modification and a	uthority)						
E. IMPORTANT: Contractor is not,	is required to si	gn this document and return	copies to the issuing	g office.			
14. DESCRIPTION OF AMENDMENT/MODIFI where feasible.) Solicitation W912P5-04-T-0026 is hereby an Replace pages C-1 and C-2 with attached No other changes.	nended to revise Sec		3	matter			
Except as provided herein, all terms and conditions of the documen							
15A. NAME AND TITLE OF SIGNER (Type or print)		16A. NAME AND TITLE OF CON	TRACTING OFFIC	ER (Type or	r print)		
		TEL:	EMAIL:				
15B. CONTRACTOR/OFFEROR	15C. DATE SIGNE	ED 16B. UNITED STATES OF AMER	ICA	10	6C. DATE S	IGNED	
	_	BY					
(Signature of person authorized to sign)		(Signature of Contracting Offi	cer)	_			

EXCEPTION TO SF 30 APPROVED BY OIRM 11-84

30-105-04

STANDARD FORM 30 (Rev. 10-83) Prescribed by GSA FAR (48 CFR) 53.243

## SECTION SF 30 BLOCK 14 CONTINUATION PAGE

#### **SUMMARY OF CHANGES**

SECTION SF 1449 - CONTINUATION SHEET

The following have been modified: SPECIFICATIONS

## SECTION C SPECIFICATIONS FOR

# REPAIR OF HYDROELECTRIC GENERATOR THRUST BEARING SHOES AND THRUST BEARING RUNNER

- 1. <u>DESCRIPTION OF WORK</u>. The Contractor shall furnish all labor, materials, plant, and equipment to place in first class condition twelve (12) generator thrust bearing shoes and one (1) thrust bearing runner in strict accordance with the requirements of these specifications. Attached sketches are FOR INFORMATION ONLY.
- 2. <u>SHIPMENT</u>. The Contractor shall pick up the shoes and runner at Wolf Creek Powerplant and deliver back to Wolf Creek Powerplant upon completion of work.
- 3. <u>BABBITT</u>. The babbitt shall be in accordance with American Society for Testing and Materials (ASTM) Standard B23-94 Alloy No. 2. The Contractor shall submit babbitt certification as required in ASTM B23 Section 11.
  - 4. DETAILS OF WORK.
  - 4.1 Thrust Bearing Shoes
- 4.1.1. The Contractor shall examine the shoes upon receipt paying special attention to the existing features of the shoe. A print shall be drafted and accurate measurements and details—shall be recorded. The existing babbitt shall be removed from—the shoes by an approved method and the surfaces shall be—properly chemically cleaned to accept babbitt.
- 4.1.2. A form, which is to be manufactured by the Contractor, shall be installed on the shoe and shoe heated to babbitt receiving temperature.
- 4.1.3. The babbitt shall be heated to pouring temperature, stirred, dross removed and poured into the shoe. Cooling shall be as prescribed by mass of shoe.
- 4.1.4. The Contractor shall manufacture a fixture to machine the shoes and a skim cut shall be taken to prepare the surface for ultrasonic testing. (The Contractor shall have in- house testing equipment for these tests.)
- 4.1.5. The ultrasonic testing must show a minimum of 95% total bond per shoe with no single defect larger than 1 square inch. The distance between any two defects shall be greater than two times the total length of any one defect. All edges must show 100% bonding.
- 4.1.6. The babbitted shoes shall be machined to the proper dimension of 44.125 inches outside radius and 27.938 inches for the inside radius. The shoes shall be finished to 32 RMS finish. Each shoe shall be checked for flatness by "blueing" to a granite surface plate. A minimum of 80% contact shall be achieved.
- 4.1.7. All edges shall be finished for proper fit. The back of the shoes shall be buffed and all threads chased.

- 4.1.8. All non-painted non-babbitted shoe surfaces shall be coated with a lubricant for corrosion protection.
- 4.1.9. The shoes shall be boxed in such a way as to protect the babbitted surface against damage during shipment.
- 4.1.10. The Contracting Officer's representative will examine the shoes after finishing but prior to shipment.

### 4.2. Thrust Bearing Runner

- 4.2.1. The Contractor shall examine the runner upon receipt, paying special attention to the existing features of the runner. A print shall be drafted and accurate measurements and details shall be recorded.
- 4.2.2. The runner is fabricated from fine grain hard cast iron. The Contractor shall dust cut runner joint faces and remachine keyways. The Contractor shall manufacture new keys for a 0.0005" to 0.0008" interference fit. The runner shall be assembled and joint screws torqued to 500 ft-lbs. The shaft mating surface shall be finished to 16 RMS. The inside diameter shall be bored to 55.750". The bearing surface shall be lapped to 8 RMS surface finish. Thickness variation of runner along a radial line shall not exceed 0.0005". The runner shall be cleaned, disassembled and joint edges shall be radiused to 0.010" to 0.015" radius.
  - 4.2.3. All non-painted runner surfaces shall be coated with a lubricant for corrosion protection.
  - 4.2.4. The runner shall be boxed in such a way as to protect it against damage during shipment.

### 5. TESTING REQUIREMENTS

- 5.1. Ultrasonic Testing (UT)
- 5.1.1. The Contractor shall ultrasonic test 100% of the babbitt area of each shoe to ensure sound bond to the base material. Testing shall be by the pulse-echo method.
- 5.1.2. The Contractor shall provide written record showing results of the testing as required by this procedure.
- 5.1.3. Frequency shall be 2.25 or 5Mhz longitudinal mode.
- 5.1.4. Crystal size shall allow good contact with the babbitt surface. Maximum diameter shall be 1-1/8". Smaller transducer may be used when further investigation of indications is required.
- 5.1.5. Reference blocks shall consist of soundly babbitted steel block with scanning surface representative of the bearing surface. The block shall be used to set the sensitivity of the instrument. A reference block with unbonded areas shall be provided for comparison of indications for areas showing bond and lack of bond.
- 5.1.6. Test sensitivity shall be such that the babbitt to base material interface is readily identified on the CRT. Details of sensitivity calibration and determination of bond and unbond areas shall be defined.
- 5.1.7. The report of the final UT examination shall contain the manufacturer's identification number, authorized signature, date, inspection procedure, test frequency, instrument, type and size of transducer employed, all areas of unbond and the location of repaired areas.
- 5.1.8. A continuous loss of back reflection greater than 50% over any single area exceeding 1% of the babbitted area shall be mapped and recorded providing the reason for loss of back reflection is unknown. Such areas shall be included in the final UT examination report.